Technical Datasheet

# FIBERGLASS MESH FOR WATERPROOFING LAYERS

## Fiberglass mesh for reinforcing waterproofing layers

### Description – Fields of application

Coated alkali-resistant fiberglass mesh 65 g/m$^2$. Used in order to locally or totally reinforce waterproofing layers (ISOFLEX, AQUAMAT-ELASTIC, AQUAMAT-FLEX etc.), in case the surface shows local or total cracks, as well as at wall-to-floor junctions, corners, etc.

### Technical data

| | |
|---|---|
| Mesh hole size: | 1 mm x 2 mm |
| Weight: | 65 g/m$^2$ |
| Tensile strength (warp/weft): | 730 (±50) N/50 mm, |
| | 565 (± 50) N/50 mm |

### Packaging

- 1 m x 50 m (50 m$^2$) rolls.
- 10 cm x 50 m rolls.

### Storage

Stored in original unopened packaging, in places protected from moisture and UV radiation, at a temperature ranging from -10ºC to +50ºC.

**ISOMAT S.A.**
BUILDING CHEMICALS, MORTARS & PAINTS
**HEADQUARTERS – THESSALONIKI, GREECE**
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
**T** +30 2310 576000
**www.isomat.eu e-mail: support@isomat.eu**

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product. | Edition: 16.11.2022