Technical Datasheet

ISOFLEX-HYBRID PU

Hybrid, elastomeric, liquid waterproofing membrane for flat roofs, based on acrylic and polyurethane resins

Description

ISOFLEX-HYBRID PU is a hybrid, elastomeric, water-based, liquid waterproofing membrane for flat roofs, based on acrylic and polyurethane resins. Has excellent adhesion to various substrates including concrete, wood, metal and any type of waterproofing membranes and is applicable even to irregular substrates. After curing, it forms an elastic waterproof and vapor-permeable membrane without seams or joints, offering:

- High elasticity.
- High resistance to weather and aging.
- High whiteness and solar reflectance.
- Improvement of building energy efficiency by decreasing the roof temperature.
- Resistance to ponding water.

ISOFLEX-HYBRID PU (white) has been successfully tested by a third-party laboratory for its high solar reflectance, which improves building energy efficiency and, in turn, reduces cooling costs, making it an ideal solution for cool roofs.
Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked. Certificate No.: 2032-CPR-10.11.

Fields of application

ISOFLEX-HYBRID PU is ideal for waterproofing flat roofs, curved roofs, etc. Constitutes a simple and safe waterproofing solution for roof details, such as corners, edges and joints between different adjacent materials, as well as for isolated cracks. Furthermore, thanks to its high solar reflectance, it can be used as a cool roof coating.

Technical data

Color:	white
Density: (EN ISO 2811-1)	1.40 kg/l
Elongation at break: (EN ISO 527-3)	550%
Water vapor permeability: (EN ISO 7783-2: Class I-permeable to water vapor, S_d < 5)	S_d = 0.59 m
Capillary water absorption: (EN ISO1062-3: W_3 low, w < 0.10 kg/m^2·h$^{0.5}$)	0.01 kg/m^2·h$^{0.5}$
Adhesion strength: (EN 1542, requirement for flexible systems with no traffic:0.8 N/mm^2)	1.9 N/mm^2
Artificial weathering: (EN 1062-11, after 2000 h)	Pass (no blistering, cracking or flaking)
Reaction to fire: (EN 13501-1)	Euroclass F
Solar Reflectance (SR): (ASTM E903-96, ASTM G159-98)	85%
Infrared Emittance ε (±0,02): (ASTM C1371-04a)	0.80
Solar Reflectance Index (SRI): (ASTM E1980-01):	106
Minimum application temperature:	+5°C
Viscosity: (EN ISO 2884-2)	≈ 30,000 mPa·s
Drying time at +20°C: (EN ISO 9117-6)	2 h (touch dry)
Recoat time at +20°C: (EN ISO 9117-6)	18 h (touch dry)

Directions for use

1. Substrate preparation
The substrate must be dry, clean, free of grease, loose particles, dust, etc. Any existing cavities in concrete should be repaired in advance. The substrate is then primed with the special primer ISO-PRIMER, with a consumption of approx. 200 g/m^2.

ISOFLEX-HYBRID PU

2. Application – Consumption

a) Full-surface waterproofing
As soon as the primer has dried, ISOFLEX-HYBRID PU is applied by brush, roller, or spray in two layers, with a consumption of 0.5-0.75 kg/m^2/layer, depending on the substrate. The second layer should be applied crosswise, after the first one has dried and is walkable.
In areas with severe cracks, it is recommended to locally reinforce ISOFLEX-HYBRID PU with a 10 cm wide strip of fiberglass mesh (65 g/m^2) or polyester fleece (30 g/m^2) along the cracks.
In that case, after the primer has dried, a layer of ISOFLEX-HYBRID PU is applied along the cracks and, while still fresh, the 10 cm wide strip of fiberglass mesh or polyester fleece is embedded lengthwise. Then, two extra layers of ISOFLEX-HYBRID PU are applied over the entire surface.

In case of dense, multiple cracks appearing all over the surface, it is strongly recommended to fully reinforce ISOFLEX-HYBRID PU membrane with 100 cm wide strips of fiberglass mesh (65 g/m^2) or polyester fleece (30 g/m^2). These placed strips must overlap by 5-10 cm. In that case, after the primer has dried, a layer of ISOFLEX-HYBRID PU is applied as wide as the upcoming reinforcement, and, while still fresh, a strip of fiberglass mesh or polyester fleece is embedded. The same application process is followed over the remaining surface. Subsequently, two extra layers of ISOFLEX-HYBRID PU are applied over the entire reinforcement.
Consumption: approx. 2.0-2.5 kg/m^2, depending on the substrate and the type of reinforcement.

b) Local waterproofing of cracks
In this case, the substrate is primed only across the cracks to a width of 10-12 cm. After the primer has dried, a layer of ISOFLEX-HYBRID PU is applied and, while still fresh, a 10 cm wide strip of fiberglass mesh (65 g/m^2) or polyester fleece (30 g/m^2) is embedded lengthwise. Then, two extra ISOFLEX-HYBRID PU layers are applied along the cracks, completely covering the reinforcement.
Consumption: approximately 200-250 g/m of crack length.

Tools should be cleaned with water while ISOFLEX-HYBRID PU is still fresh.

Packaging

ISOFLEX-HYBRID PU is supplied in 1 kg, 4 kg, 13 kg and 25 kg containers.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory i, type WB is 140 g/l (2010) for the ready-to-use product.
The ready-to-use product ISOFLEX-HYBRID PU contains 8 g/l VOC.

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Research and Development Department of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product. | Edition: 01.04.2026

ISOFLEX-HYBRID PU

CE

2032

ISOMAT S.A.
17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag Athanasios, Greece

25

2032-CPR-10.11

DoP No.: ISOFLEX-HYBRID PU/ 1445-01

EN 1504-2

Surface protection products

Coating

Permeability to CO_2: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: w < 0.1 kg/m^2·h$^{0.5}$

Adhesion strength by pull off test: ≥ 1.0 N/mm^2

Artificial weathering: No visual defects

Reaction to fire: Euroclass F

Dangerous substances comply with 5.3

ISOMAT S.A.
BUILDING CHEMICALS, MORTARS & PAINTS
HEADQUARTERS – THESSALONIKI, GREECE
17th km Thessaloniki – Ag. Athanasios Road
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece
T +30 2310 576000
www.isomat.eu e-mail: support@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Research and Development Department of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product. | Edition: 01.04.2026